

CLAIMS

- 5 1. A knitted fabric (12), comprising fibres, at least part of these fibres being metal fibres, said fabric having 90 or more stitches per square centimetre.
2. A knitted fabric according to claim 1, said fabric having 100 or more stitches per square centimetre.
- 10 3. A knitted fabric according to claims 1 to 2, having an air permeability higher than $2400 \text{ l/10cm}^2\cdot\text{h}$.
4. A knitted fabric according to claims 1 to 2, having a weight between 600 g/m^2 and 2000 g/m^2 .
5. A knitted fabric according to claims 1 to 2, having a thickness more than 0.8 mm.
- 20 6. A knitted fabric of claim 1 to 5, all of said fibres being metal fibres.
7. A knitted fabric of claim 1 to 6, all of said fibres are stainless steel fibres.
- 25 8. A knitted fabric of claim 7, in which the stainless steel contains at least 16% Cr and 10% Ni.
9. A knitted fabric of claim 1 to 8, having the single jersey 1/2 structure (23).
- 30 10. A knitted fabric of claim 1 to 8, having the single jersey 1/3 structure (28).

T
E
X
T
I
L
E
S
O
F
T
W
A
R
E

- 5
11. A knitted fabric of claim 1 to 8, having the single jersey 1/4 structure (32).
12. A knitted fabric of claim 1 to 11, obtainable by means of a knitting machine with gauge equal or more than 20.
13. A knitted fabric of claim 1 to 11 obtainable by means of a knitting machine with gauge equal or more than 22.
- 10
15
14. A knitted fabric of claim 1 to 13, comprising yarns with metrical number equal or larger than 5.5.
15. A knitted fabric of claim 1 to 13, comprising yarns with metrical number equal or larger than 7.5.
16. A knitted fabric of claim 1 to 13, comprising yarns with metrical number equal or larger than 10.
- 20
17. Use of a fabric according to any one of the preceding claims for covering moulds and tempering or press-on rings which are utilised in the process of forming glass plates, or for covering the means of transport by which glass plates are moved during the forming process.
- 25
18. A method to reducing the risk for marking on a glass plate during bending of the glass plate, said method comprising the steps :
(a) providing fibres, at least part of these fibres being metal fibres,
(b) knitting said fibres into a fabric, such that said fabric has 90 or more stitches per square centimetre.
- 30